

# Ayton C60B3

## Technical Data Sheet



## Cold Applied Surface Dressing / Spray Injection Patching Emulsion

### GENERAL

Ayton C60B3 is a cationic bitumen emulsion which complies with grade C60B3 of EN 13808:2013. It has been designed for use as a surface treatment cold applied surface dressing / spray injection patching bitumen emulsion.

Ayton C60B3 is manufactured by Ayton Products within Management Systems accredited to ISO 9001:2015, ISO 14001:2015 and ISO 45001:2018.

### SURFACING DESIGN

The design and implementation of surfacing using Ayton C60B3 should be carried out in accordance with Design Manual for Roads and Bridges Volume 7 Section 5 Part 2: HD 37/99.

### HEALTH AND SAFETY

Ayton C60B3 is classified as hazardous to the aquatic environment. For further information refer to our relevant Material Safety Data Sheet or contact our Safety, Health and Environment Department.

### SUPPLY

Availability, prices and conditions of sale are available from our Bitumen Products Sales Department.

### TECHNICAL SERVICE

Further technical information and advice is available from our Technical Department.

Product code:	C60B3
Revision:	03
Reviewed:	20.08.19
Next review:	31.12.21
Page:	1 of 2



Ayton Products is a trading name of Kier Integrated Services Limited

Browick Road, Wymondham, Norfolk, NR18 0RJ

Tel: 01953 602002 Fax: 01953 609864 [www.ayton.co.uk](http://www.ayton.co.uk) [www.kier.co.uk](http://www.kier.co.uk)

# Ayton C60B3

## Technical Data Sheet



### Cold Applied Surface Dressing / Spray Injection Patching Emulsion

<b>Cationic bituminous emulsion: Ayton C60B3 C60B3 to EN 13808:2013</b>		
Viscosity (dynamic)	20 - 300 mPa.s (Class 10)	EN 13302
Water effect on binder adhesion	≥ 75 % (Class 2)	EN 13614
Breaking behaviour	70 - 155 (Class 3)	EN 13075-1 (Forshammar)
Dangerous substances	NPD	-
<b>Residual binder recovered by evaporation from cationic bituminous emulsion according to EN 13074 -1</b>		
Consistency at intermediate service temperature	≤ 330 x 0.1 mm (Class 7)	EN 1426
Consistency at elevated service temperature	≥ 35 °C (Class 8)	EN 1427
Cohesion	NR (Class 0)	EN 13588
<b>Durability Stage 1 Binder recovered by evaporation (EN 13074-1) and subjected to stabilisation (EN 13074 -2)</b>		
Durability of consistency at intermediate service temperature	≤ 220 x 0.1 mm (Class 5)	EN 1426
Durability of consistency at elevated service temperature	≥ 35 °C (Class 8)	EN 1427
Durability of cohesion	NR (Class 0)	EN 13588
<b>Durability Stage 2 Binder recovered by evaporation (EN 13074-1) and subjected to stabilisation (EN 13074 -2) and ageing (EN 14769)</b>		
Durability of consistency at intermediate service temperature	NPD	EN 1426
Durability of consistency at elevated service temperature	NPD	EN 1427
Durability of cohesion	NR (Class 0)	EN 13588

Product code: C60B3  
Revision: 03  
Reviewed: 20.08.19  
Next review: 31.12.21  
Page: 2 of 2



Ayton Products is a trading name of Kier Integrated Services Limited

Browick Road, Wymondham, Norfolk, NR18 0RJ

Tel: 01953 602002 Fax: 01953 609864 [www.ayton.co.uk](http://www.ayton.co.uk) [www.kier.co.uk](http://www.kier.co.uk)